SGS United Kingdom Ltd.
Testing Division

Oakwood House,
City Road,
Bradford,
West Yorkshire, BD8 8JY
Tel:- 01274 394980
Fax:- 01274 729401
Telex: 51445

Lows of Dundee Ltd
6 South Ward Road
DUNDEE
Tayside, DD1 1PN

27 JAN 1998

Attn: Mr Duncan Petrie

Certificate No. BTX 11506/PCF/98

Date : 26 January 1998 Page 1/2 Your Ref. : P/Order LD.6811

REPORT ON SAMPLE SUBMITTED ON 16 January 1998

Quality PE550/FR/ML fabric

Flammability in accordance with the requirements of Home Office "Guide t Fire Precautions in Existing Places of Entertainment and Like Premises"

Requirements: Chapter 13 para 13.18 for "temporary structures" require that for any set of six specimens, when tested using BS5438:1989 Tests 2A and 2B, no part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of the specimen, and there shall be no separation of flaming debris. If only one specimen fails, then a further six specimens shall be tested. All additional six specimens shall meet the requirements for the sample to pass.

Flammability of textile fabrics when subjected to a small igniting flame applied to the face or bottom edge of vertically oriented specimens: Determination of limited flame spread (BS5438:1989)

Test 2A using a 10 seconds flame application time applied to the fabric face.

Test 2B using a 10 seconds flame application time applied to bottom edge of the fabric.

Conditioning:

The samples were conditioned in an atmosphere having a temperature of 20 ± 5°C and a relative humidity of 65 ± 5%.

Test specimens:

The specimens were tested in the "as received" condition only.

Continued ../2

Enquiries relating to the content of this report to be directed to the Reporting Officer.